

CALIBRE™ 201-22

Polycarbonate Resin

Overview

CALIBRE™ 200-22 polycarbonate resins are produced in compliance with the US Food and Drug Administration (FDA) and EU food contact regulations. They provide excellent impact resistance, heat distortion resistance and optical clarity. The CALIBRE 200-22 series products are available in 4 additive packages: CALIBRE 200: No mold release or UV Stabilizer. CALIBRE 201: Mold release. CALIBRE 202: UV stabilizer. CALIBRE 203: Mold release and UV stabilizer. . (Note that CALIBRE 202 and 203 grades are not available in Europe and do not comply with EU food contact regulations).

Govt. and Industry Standards:

- U.S. FDA 21 CFR 177.1580
- CSA
- Underwriters Laboratory (UL)
- EU food contact 2002/72/EC

Applications

- Food processors
- Beverage containers
- Food utensils
- Other packaging applications

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.20 g/cm ³	1.20 g/cm ³	ASTM D792 ISO 1183/A
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	22 g/10 min	22 g/10 min	ASTM D1238 ISO 1133
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3 in/in	0.50 to 0.70 %	ASTM D955 ISO 294-4
Water Absorption			ASTM D570 ISO 62
73°F (23°C), 24 hr	0.15 %	0.15 %	
Equilibrium, 73°F (23°C), 50% RH	0.32 %	0.32 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus			
--	340000 psi	2340 MPa	ASTM D638 ¹
--	334000 psi	2300 MPa	ISO 527-2/50
Tensile Strength			
Yield	8700 psi	60.0 MPa	ASTM D638 ¹ ISO 527-2/50 ^{1, 1}
Break	9500 psi	65.5 MPa	ASTM D638 ¹
Break	9570 psi	66.0 MPa	ISO 527-2/50
Tensile Elongation (Break)	120 %	120 %	ISO 527-2/50 ASTM D638 ¹
Flexural Modulus			
--	350000 psi	2410 MPa	ASTM D790 ²
--	348000 psi	2400 MPa	ISO 178 ³
Flexural Strength			
--	14000 psi	96.5 MPa	ASTM D790 ²
--	14100 psi	97.0 MPa	ISO 178 ³
Taber Abrasion Resistance	45 %	45 %	ASTM D1044

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			
73°F (23°C)	14 ft-lb/in	750 J/m	ASTM D256
73°F (23°C)	35 ft-lb/in ²	74 kJ/m ²	ISO 180/A
Unnotched Izod Impact (73°F (23°C))	No Break	No Break	ASTM D256 ISO 180
Instrumented Dart Impact			ASTM D3763 ⁴
73°F (23°C), Total Energy	640 in-lb	72.3 J	
Tensile Impact Strength	180 ft-lb/in ²	378 kJ/m ²	ASTM D1822
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness			ASTM D785
M-Scale	72	72	
R-Scale	118	118	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	282 °F	139 °C	ISO 75-2/B
66 psi (0.45 MPa), Annealed	288 °F	142 °C	ASTM D648 ISO 75-2/B
264 psi (1.8 MPa), Unannealed	258 °F	126 °C	ASTM D648
264 psi (1.8 MPa), Annealed	282 °F	139 °C	ASTM D648
264 psi (1.8 MPa), Annealed	259 °F	126 °C	ISO 75-2/A
Vicat Softening Temperature	297 °F	147 °C	ISO 306/B50 ASTM D1525 ⁵
Ball Indentation Temperature	257 °F	125 °C	IEC 60335-1
CLTE - Flow (-40 to 180°F (-40 to 82°C))	3.8E-5 in/in/°F	6.8E-5 cm/cm/°C	ASTM D696
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Volume Resistivity	2.0E+17 ohm·cm	2.0E+17 ohm·cm	ASTM D257
Dielectric Strength			
--	420 V/mil	17 kV/mm	ASTM D149
--	430 V/mil	17 kV/mm	IEC 60243-1
Dielectric Constant			ASTM D150
60 Hz	3.00	3.00	
1 MHz	3.00	3.00	
Dissipation Factor			ASTM D150
50 Hz	1.0E-3	1.0E-3	
1 MHz	2.0E-3	2.0E-3	
Comparative Tracking Index			IEC 60112
0.0787 in (2.00 mm), Solution A	250 V	250 V	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94 ⁶
0.0626 in (1.59 mm)	HB	HB	
0.126 in (3.20 mm)	HB	HB	
Oxygen Index	26 %	26 %	ISO 4589-2 ⁶
Average Extent of Burning	1 in	3 cm	ASTM D635
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Refractive Index	1.586	1.586	ASTM D542 ISO 489
Transmittance	89.0 %	89.0 %	ASTM D1003
Haze	1.0 %	1.0 %	ASTM D1003

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ 2.0 in/min (50 mm/min)

² Method I (3 point load), 0.079 in/min (2.0 mm/min)

³ 0.079 in/min (2.0 mm/min)

⁴ 11.1 ft/sec (3.39 m/sec)

⁵ Rate A (50°C/h), Loading 2 (50 N)

⁶ This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.

Product Stewardship

Styron LLC, Styron HoldCo B.V., and subsidiaries ("Styron") have a fundamental concern for all who make, distribute, and use its products and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health and environmental information on our products to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Styron products – from the initial concept and research, to manufacture, use, sales, disposal and recycle of each product

Customer Notice

Customers are responsible for reviewing their manufacturing processes and their applications of Styron products from the standpoint of human health and environmental quality to ensure that Styron products are not used in ways for which they are not suitable. Styron personnel are available to answer questions and to provide reasonable technical support. Styron product literature, including safety data sheets, should be consulted prior to the use of Styron products. Current safety data sheets are available from Styron.

Notice Regarding Medical Application Restrictions

Styron requests that customers considering the use of Styron products in medical applications notify Styron so that appropriate assessments may be conducted.

Styron does not endorse or claim suitability of its products for specific medical applications and does not knowingly sell or sample its products or services for certain medical applications. It remains the responsibility of the medical device or pharmaceutical manufacturer to determine that the Styron product is safe, lawful, and technically suitable for the intended use.

Disclaimer

No freedom from infringement of any patent owned by Styron or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. **STYRON ASSUMES NO OBLIGATION OR LIABILITY FOR THE INFORMATION IN THIS DOCUMENT. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

If products are described as "experimental" or "developmental": 1.) product specifications may not be fully determined; 2.) analysis of hazards and caution in handling and use are required; 3.) there is greater potential for Styron to change specifications and/or discontinue production; and 4.) although Styron may from time to time provide samples of such products, Styron is not obligated to supply or otherwise commercialize such products for any use of application whatsoever.

Responsible Care®

Our top priority is to provide the highest quality products and services, and to focus on the American Chemistry Council's Responsible Care® initiative and safety in all of our facilities.

Additional Information

North America		Europe/Middle East	+800 444 11 444
U.S. & Canada:	1-888-STYRON1		+31-11567-2626
	1-989-633-1718	Germany:	+8001811361
Mexico:	+1-800-441-4369		
Latin America		Asia Pacific	+800-7776-7776
Argentina:	+54-11-4319-0100		+603-7965-5319
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000		
Mexico:	+52-55-5201-4700		

www.styron.com

This document is intended for use within Europe, Latin America, North America

Published: July 2014

© 2014 Styron LLC, Styron HoldCo B.V., and subsidiaries

